



Texdecor - Casamance
2, rue d'Hem
59780 WILLEMS
France

Your notice of
 09-08-2024

Your reference

Date
 06-09-2024

Analysis Report 24.04291.08

Required tests :
NFPA 260 (2024)


Tests and Classification System for Cigarette Ignition
Resistance of Components of Upholstered Furniture - Cover
Fabric Test

Sample id	Information given by the client	Date of receipt
T2415915	4737	09-08-2024



Gina Créelle
 Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Samples

T2415915
4737





Reference: T2415915 - 4737

Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture - Cover Fabric Test

Date of ending the test 04-09-2024
Standard used NFPA 260 (2024)

Deviation from the standard -

Conditioning 23°C, relative humidity 50%
Testing atmosphere 22°C, relative humidity 65%

The test was carried out in accordance with NFPA 260 § 6.2

Filling T 30125 (Recticel) - non-fire retardant foam
Cover Sheeting Material Composition 100 % cotton
weight (125 ± 28) g/m²

	1	2	3
Open flaming	no	no	no
Ignition of the test specimen	no	no	no
Smoulders more than 45 min.	no	no	no
Vertical char length $\geq$ 45 mm	no	no	no

Cover Fabric Classification

CLASS I	- no open flaming - no evidence of ignition of any test assembly - no smouldering after 45 minutes - vertical char on any of the three specimens shall not exceed 44 mm.
CLASS II	- cover fabrics that do not meet Class I criteria

Conclusion **Class I**